

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

AS22759/8

FEDERAL SUPPLY CLASS
6145


NOTICE

THIS DOCUMENT HAS BEEN TAKEN DIRECTLY FROM U.S. MILITARY SPECIFICATION MIL-W-22759/8B, NOTICE 1, AMENDMENT 2 AND CONTAINS ONLY MINOR EDITORIAL AND FORMAT CHANGES REQUIRED TO BRING IT INTO CONFORMANCE WITH THE PUBLISHING REQUIREMENTS OF SAE TECHNICAL STANDARDS. THE INITIAL RELEASE OF THIS DOCUMENT IS INTENDED TO REPLACE MIL-W-22759/8B, NOTICE 1, AMENDMENT 2. ANY PART NUMBERS ESTABLISHED BY THE ORIGINAL SPECIFICATION REMAIN UNCHANGED.

THE ORIGINAL MILITARY SPECIFICATION WAS ADOPTED AS AN SAE STANDARD UNDER THE PROVISIONS OF THE SAE TECHNICAL STANDARDS BOARD (TSB) RULES AND REGULATIONS (TSB 001) PERTAINING TO ACCELERATED ADOPTION OF GOVERNMENT SPECIFICATIONS AND STANDARDS. TSB RULES PROVIDE FOR (A) THE PUBLICATION OF PORTIONS OF UNREVISED GOVERNMENT SPECIFICATIONS AND STANDARDS WITHOUT CONSENSUS VOTING AT THE SAE COMMITTEE LEVEL, AND (B) THE USE OF THE EXISTING GOVERNMENT SPECIFICATION OR STANDARD FORMAT.

UNDER DEPARTMENT OF DEFENSE POLICIES AND PROCEDURES, ANY QUALIFICATION REQUIREMENTS AND ASSOCIATED QUALIFIED PRODUCTS LISTS ARE MANDATORY FOR DOD CONTRACTS. ANY REQUIREMENT RELATING TO QUALIFIED PRODUCTS LISTS (QPL'S) HAS NOT BEEN ADOPTED BY SAE AND IS NOT PART OF THIS SAE TECHNICAL DOCUMENT.

THIRD ANGLE PROJECTION



ISSUED 2000-09

PREPARED BY SAE SUBCOMMITTEE AE-8D

SAE The Engineering Society
For Advancing Mobility
INTERNATIONAL
Land Sea Air and Space®
400 Commonwealth Drive, Warrendale, PA 15096-0001


AEROSPACE STANDARD

WIRE, ELECTRIC, FLUOROPOLYMER-INSULATED,
ABRASION RESISTANT EXTRUDED PTFE, MEDIUM
WEIGHT, NICKEL-COATED COPPER CONDUCTOR, 600 VOLT

AS22759/8
SHEET 1 OF 4

THE COMPLETE REQUIREMENTS FOR PROCURING THE WIRE DESCRIBED HEREIN SHALL CONSIST OF THIS DOCUMENT AND THE ISSUE IN EFFECT OF SPECIFICATION MIL-W-22759.

AS22759/8



Note: Outer surface is smooth, homogeneous PTFE with no mineral filler exposed.

TABLE I. CONSTRUCTION DETAILS.

Part No. 1/	Wire size	Stranding (Number of strands X AWG gage of strands)	Diameter of stranded conductor (inches)		Finished wire		
			(min)	(max)	Resistance at 20°C (68°F) (ohms/1000 ft) (max)	Diameter (inches)	Weight (lbs/1000 ft) (max)
M22759/8-24-*	24	19 X 36	.023	.026	25.9	.062 ±.002	4.3
M22759/8-22-*	22	19 X 34	.029	.033	16.0	.073 ±.002	6.0
M22759/8-20-*	20	19 X 32	.037	.041	9.77	.082 ±.002	8.1
M22759/8-18-*	18	19 X 30	.046	.051	6.10	.092 ±.002	11.0
M22759/8-16-*	16	19 X 29	.052	.058	4.76	.102 ±.003	13.8
M22759/8-14-*	14	19 X 27	.065	.073	3.00	.115 ±.003	18.6
M22759/8-12-*	12	19 X 25	.082	.092	1.89	.134 ±.003	28.5
M22759/8-10-*	10	37 X 26	.106	.114	1.24	.158 ±.004	41.8
M22759/8-8-*	8	133 X 29	.158	.173	.594	.220 ±.005	73.1
M22759/8-6-*	6	133 X 27	.198	.217	.436	.270 ±.006	113.
M22759/8-4-*	4	133 X 25	.250	.274	.275	.328 ±.007	173.

1/ PART NO.: The asterisks in the part number column, Tables I through III, shall be replaced by color code designators in accordance with MIL-STD-681. Examples: Size 20, white - M22759/8-20-9; white with orange stripe - M22759/8-20-93.

TABLE II. PERFORMANCE DETAILS.

Part No.	Abrasion resistance					Bend testing			
	Proced- ure	Resistance (inches of tape) (min) (initial and after immersion)	Weight support bracket	Weight (lbs)	Tension load (lbs)	Mandrel diameter (inches) (+3%)		Test load (lbs) (+3%)	
						Life cycle (oven & bend tests) <u>1/</u>	Cold bend test	Life cycle (oven & bend tests) <u>1/</u>	Cold bend test
M22759/8-24-*	II	48	A	3.0	1.0	4.5	3.0	.75	2.0
M22759/8-22-*	II	54	A	3.0	1.0	4.5	3.0	.75	2.0
M22759/8-20-*	II	66	A	3.0	1.0	4.5	3.0	.75	2.0
M22759/8-18-*	II	72	A	3.0	1.0	4.5	3.0	1.00	2.0
M22759/8-16-*	II	81	A	3.0	1.0	6.5	3.0	1.00	3.0
M22759/8-14-*	II	81	A	4.25	2.0	6.5	3.0	3.00	3.0
M22759/8-12-*	II	81	B	4.25	2.0	6.5	6.0	3.00	3.0
M22759/8-10-*	II	81	B	4.25	2.0	10.0	6.0	3.00	5.0
M22759/8-8-*	I	25	B	3.0	2.0	10.0	6.0	3.00	6.0
M22759/8-6-*	I	25	C	3.0	2.0	10.0	6.0	3.00	6.0
M22759/8-4-*	I	33	C	4.25	2.0	10.0	6.0	6.00	10.0

1/ Also for bend tests after immersion.

ADDITIONAL REQUIREMENTS

TEMPERATURE RATING: 260°C (500°F) max conductor temperature

VOLTAGE RATING: 600 volts (rms) at sea level

SPARK TEST OF PRIMARY INSULATION: Not required

IMPULSE DIELECTRIC TEST: 8.0 kilovolts (peak), 100% test

INSULATION RESISTANCE: 50,000 megohms for 1000 ft (min)

WRAP TEST:

"Wrap back" test required; no cracking

Oven temperature; 313 ±2°C (595.4 ±3.6°F)

BLOCKING: 260 ±2°C (500 ±3.6°F)

SHRINKAGE: 0.125 inch max at 313 ±2°C (595.4 ±3.6°F)

WICKING (PROCEDURE I): 1.0% (max) weight increase

LOW TEMPERATURE (COLD BEND):

Bend temperature: -65 ±2°C (-85 ±3.6°F)

Dielectric test, 3000 volts (rms), 60Hz

THERMAL SHOCK:

Oven temperature, 260 ±2°C (500 ±3.6°F)

Max change in measurement

Sizes 24 through 12: 0.060 inch

Sizes 10 through 8: 0.100 inch

Sizes 6 through 4: 0.125 inch

FLAMMABILITY: Post-flame dielectric test not required

LIFE CYCLE:

Oven temperature 313 ±2°C (595.4 ±3.6°F)

Dielectric test, 2500 volts (rms), 60Hz

DIELECTRIC TEST AFTER IMMERSION: 3000 volts (rms), 60 Hz

ACID RESISTANCE:

Not required

Dielectric test, 3000 volts (rms), 60 Hz

CONDUCTOR STRAND ADHESION REQUIREMENTS: Shall be in accordance with 3.6.11 of MIL-W-22759.

ABRASION RESISTANCE AFTER IMMERSION: Specimens after immersion shall meet the same abrasion requirements as initial specimens; this test to be a quality conformance test subject to the same inspection level and acceptable quality level as the test for initial abrasion resistance.

HUMIDITY RESISTANCE: 50,000 megohms for 1000 ft, min insulation resistance after humidity exposure

SURFACE RESISTANCE: 500 megohm-inches (min), initial and final readings.

SMOKE: 313°C (595.4°F)

COLOR: In accordance with MIL-STD-104, Class 1; white preferred

COLOR STRIPING OR BANDING DURABILITY: 250 cycles (500 strokes) (min), 500 grams weight

IDENTIFICATION DURABILITY: 125 cycles (250 strokes) (min), 500 grams weight

WIRE LENGTH REQUIREMENTS: Schedule A

SUPERSESSON DATA: The wire of this specification sheet, by part number, replaces and supersedes the wire of MS18001(ASG) (canceled) in accordance with Table III.

TABLE III. SUPERSESSON BY PART NUMBER

Part number MS18001 (ASG)	Part number MIL-W-22759/8
MS18001-24-*	M22759/8-24-*
MS18001-22-*	M22759/8-22-*
MS18001-20-*	M22759/8-20-*
MS18001-18-*	M22759/8-18-*
MS18001-16-*	M22759/8-16-*
MS18001-14-*	M22759/8-14-*
MS18001-12-*	M22759/8-12-*
MS18001-10-*	M22759/8-10-*
MS18001-8-*	M22759/8-8-*
MS18001-6-*	M22759/8-6-*
MS18001-4-*	M22759/8-4-*